

Properties of Particleboard Manufactured from Commonly Utilized Malaysian Bamboo (*Gigantochloa scortechinii*)

JAMALUDIN KASIM,¹ ABD. JALIL HJ. AHMAD,¹ JALALUDIN HARUN,² Zaidon Ashari² Abd. Latif Mohmod³ & Mohd Nor Mohd Yusof³

¹Department of Woods Industries, Faculty of Applied Sciences, MARA Universiti of Technology, Jengka Campus, 26400 Jengka, Pahang, Malaysia

²Department of Wood Science and Technology, Faculty of Forestry, Universiti Putra Malaysia, 43400 Serdang, Selangor

³Non-wood Division, Forest Research Institute Malaysia, 52109 Kepong, Kuala Lumpur, Malaysia

Keywords: *Gigantochloa scortechinii*, urea-formaldehyde, particleboard, age, particle size, resin, board density

ABSTRACT

Buluh semantan (Gigantochloa scortechinii), one of the most widespread bamboo species in Peninsular Malaysia was investigated for its suitability as a raw material for particleboard production. A total of 120 bamboo culms from three different age group (1-, 2 and 3-y-old) were harvested from managed bamboo clumps in FRIM. The bamboo particles produced from the flaking process were used in the making of single- and three-layer urea formaldehyde particleboards. The particleboard produced were then tested for their mechanical properties and dimensional stability according to British Standard Methods. The result showed that age, resin content and board density significantly affected the single-layer particleboard properties, while for three-layer particleboard the effect of age, core particle size and wax addition on the board properties were also found to be significant. Irrespective of bamboo age, particles of Gigantochloa scortechinii are suitable for the manufacture of urea formaldehyde particleboards.

ABSTRAK

Buluh semantan (Gigantochloa scortechinii) salah satu buluh yang terdapat secara meluas di Semenanjung Malaysia telah diselidiki akan kebolegunaannya sebagai bahan mentah untuk penghasilan papan serpai. Sejumlah 120 batang buluh yang terhasil daripada proses pengempingan kemudian digunakan untuk pembuatan papan serpai. Papan serpai yang dihasilkan diuji sifat kekuatan dan kestabilan mengikut piawaian tatacara British. Keputusan ujian menunjukkan umur, kandungan perekat dan ketumpatan papan serpai mempengaruhi dengan ketara sifat papan serpai satu lapis manakala bagi papan serpai tiga lapis, kesan umur, saiz partikel kor dan penambahan lilin ke atas sifat papan serpai juga dipengaruhi secara ketara. Tidak kira peringkat umur buluh, partikel dari buluh semantan sesuai sebagai bahan mentah untuk penghasilan papan serpai urea formaldehid.

INTRODUCTION

Malaysian bamboo is classified as a minor forest product and is traditionally considered as a weed interfering with the normal regeneration, development and maintenance of the main timber species (Medway 1973; Ng 1980; Salleh and Wong 1987). In the past, attempts were made to control their growth but now, due to the rapid extension of bamboo-based industries, they have become the second most important non-timber

produce in Malaysia after rattan (Aminuddin Abd. Latif 1991). They played an important role in the lives of the local people, particularly those in the rural areas and are usually being used for making basket-ware, cords and toys, furniture and houses. The bamboo industry has developed into a multi-million dollar industry with their products enjoying very high demand domestically as well as internationally. However, in producing the various products, much bamboo

wastes is generated, excluding those that are discarded during harvesting and transporting; and if no action is taken the bamboo would be heading towards its downfall. Therefore, the optimum use of this resource lies in the production of reconstituted products such as particleboard. With the abundant amount of bamboo resources that are currently being underutilized as well as the need to improve panel product properties and development, particleboards offer tremendous potential and opportunity towards its fullest utilization. This paper highlights the properties of single- and three-layered urea formaldehyde particleboards produced from *G. scortechinii*. The effect of age, board density, core particle size and resin content on the board properties are discussed.

MATERIALS AND METHODS

Forty culms each from 1- 2- and 3-y-old *G. Scortechinii* were obtained from the bamboo plantation of Forest Research Institute of Malaysia (FRIM), Kepong, Selangor. All branches present were removed and the clean culms were subjected to longitudinal splitting. Each age group of bamboo splits were then fed into a Pallman drum chipper. The chips produced were then flaked in a Pallman knife-ring flaker and the particles produced were screened into 0.5, 0.5-1.0, 1.0-2.0 and >2.0 mm sizes before being oven-dried at 60° C to a moisture content of about 5%.

Single-layer particleboard of 12 mm thickness of size 340× 340 mm was made at three density level (561, 641, and 721 kg/m³ and three resin contents of 8, 10 and 12%. A measured quantity of flakes was sprayed with a resin mix containing urea-formaldehyde (solid content of 65%), hardener and water within a glue blender. The particles used consisted of 60% of 1.0-2.0 mm, 30% of 0.5-1.0 mm and 10% of > 2.0 mm particle size. The sprayed particles were then laid in a wooden mould and prepressed at 3.5 MPa for about 30 seconds. The consolidated mat was finally pressed for 6 minutes at 160°C in a Taihei hot-press at 120 kg/cm².

Three-layer particleboard of 12 mm thickness of size 340 × 340 mm at a density of 721 kg/m³ were made from two different particle size (1.0 and 2.0 mm) for the core materials and 0.5 mm particle size for the surface materials. Resin content of 12% was used for the surface materials and 10% for the core. An amount of 1% wax

content (65% solid content) was added to the mixture. Three boards were produced for both the single- and three-layer particleboards for each combination of density level and resin content used.

The strength and dimensional properties, viz. thickness swelling (TS), water absorption (WA), modulus of rupture (MOR), modulus of elasticity (MOE) and internal bond (IB) were tested according to the British Standard: BS EN (1993). Screw-withdrawal edge (SWE) and screw-withdrawal surface (SWS) were tested according to the BS 5669 (1989).

RESULTS AND DISCUSSION

Single-layer Particleboard

The strength and dimensional properties of single-layer particleboard are shown in Table 1. All boards produced with a minimum resin content of 8% at a board density of 641 kg/m³ were able to meet the minimum strength requirement of BS 5669. Boards made from one year-old bamboo particles with a 12% resin and a density of 721 kg/m³ were observed to possess the highest values of MOR (28.52 MPa) and MOE (3613 MPa), two-year-old bamboo had the highest IB (1.11 MPa) while three-year-old having the highest SWS (957 N) and SWE (676 N) values. In general, bamboo particleboard produced from one year-old and older; and with the combination of more than 8% resin content (board density > 641 kg/m³) surpassed the minimum strength requirement of the BS. However, only boards produced from one year-old bamboo at a density of 561 kg/m³ and a resin content of 12% was able to meet the TS requirement of 8.0%. All other boards failed to do so.

The summary of analysis of variance (ANOVA) on the effect of age, resin content and board density on the particleboard properties are shown in Table 2. All the main variables of age, density and resin have significant effects on all the board properties.

Age showed a significant effect on all the board properties (Table 3). Jamaludin *et al.* (1997) also found a similar pattern in their study of particleboard from *Bambusa vulgaris*. Correlation analysis (Table 4) further revealed that the WA and MOR decreased insignificantly, while MOE and TS increased insignificantly with age. However, the strength properties of IB, SWS and SWE were observed to increase significantly with age. According to Moslemi (1974)

the adhesive spread per unit area of the particles could be the controlling factor on the effect of age on the strength and dimensional properties of particleboard.

Increments of resin content showed significant effect on all the board properties (Table 3). The correlation analysis also indicates that MOR, MOE, IB, SWS, and SWE increased significantly while WA and TS decreased with an increase in resin content. With more resin available at higher resin content, more bonding sites are made available, thus improving the strength properties and increased their dimensional sta-

bility, significantly. Similar observations on the strength properties-resin contents relationship were also reported by other work on wood (Talbot & Maloney 1957, Moslemi 1974, Kelly 1976), bamboo (Chen *et al.* 1991) and oil palm fruit bunches (Shaikh *et al.* 1997).

The strength and dimensional properties of particleboard are directly influenced by board density (Moslemi 1974). This is particularly true since higher density is usually associated with higher strength properties. Table 3 shows that all the MOR, MOE, IB, SWS and SWE values increase with a linear increase in board density.

TABLE 1
Physical and strength properties of single-layer UF particleboards

| Age (yrs) | Resin (%) | Board Density (kg/m ³) | MOR (MPa) | MOE (MPa) | IB (MPa) | SWS (N) | SWE (N) | WA (%) | TS (%) | |
|-----------|-----------|------------------------------------|-----------|-----------|----------|---------|---------|--------|--------|-------|
| 1 | 8 | 561 | 9.18 | 1598 | 0.23 | 182 | 137 | 38.48 | 1077 | |
| | | | 10 | 9.91 | 1675 | 0.32 | 2.15 | 163 | 36.41 | 8.50 |
| | | | 12 | 11.32 | 1734 | 0.44 | 249 | 169 | 34.22 | 7.31 |
| | 8 | 641 | 15.83 | 2480 | 0.39 | 539 | 417 | 63.57 | 24.46 | |
| | | | 10 | 20.21 | 2759 | 0.59 | 458 | 461 | 51.89 | 13.84 |
| | | | 12 | 18.03 | 2649 | 0.67 | 598 | 526 | 49.39 | 11.57 |
| | 8 | 721 | 21.33 | 3059 | 0.50 | 535 | 458 | 52.31 | 23.88 | |
| | | | 10 | 24.40 | 3330 | 0.68 | 684 | 545 | 42.91 | 15.08 |
| | | | 12 | 28.52 | 3613 | 0.69 | 719 | 622 | 36.33 | 12.42 |
| 2 | 8 | 561 | 9.77 | 1759 | 0.39 | 307 | 223 | 49.07 | 16.39 | |
| | | | 10 | 11.27 | 1896 | 0.51 | 358 | 275 | 41.27 | 11.96 |
| | | | 12 | 13.37 | 2083 | 0.61 | 405 | 325 | 36.00 | 7.60 |
| | 8 | 641 | 17.87 | 2891 | 0.66 | 542 | 428 | 59.89 | 22.18 | |
| | | | 10 | 20.98 | 3071 | 0.78 | 583 | 497 | 53.80 | 16.21 |
| | | | 12 | 21.04 | 2989 | 0.94 | 711 | 549 | 45.94 | 13.40 |
| | 8 | 721 | 17.37 | 2542 | 0.77 | 656 | 484 | 48.38 | 20.45 | |
| | | | 10 | 23.94 | 3214 | 0.99 | 788 | 616 | 40.20 | 15.17 |
| | | | 12 | 22.04 | 3132 | 1.11 | 747 | 655 | 36.85 | 11.54 |
| 3 | 8 | 561 | 11.56 | 1985 | 0.48 | 489 | 358 | 52.68 | 17.16 | |
| | | | 10 | 12.52 | 1959 | 0.45 | 476 | 376 | 45.75 | 11.07 |
| | | | 12 | 13.68 | 2168 | 0.67 | 531 | 381 | 34.93 | 9.17 |
| | 8 | 641 | 17.05 | 2538 | 0.58 | 629 | 459 | 46.43 | 17.81 | |
| | | | 10 | 17.95 | 2684 | 0.72 | 558 | 497 | 39.52 | 11.60 |
| | | | 12 | 19.12 | 2913 | 0.86 | 663 | 471 | 34.09 | 10.55 |
| | 8 | 721 | 18.28 | 2696 | 0.71 | 724 | 576 | 42.40 | 20.94 | |
| | | | 10 | 20.21 | 2934 | 0.88 | 803 | 574 | 37.16 | 12.69 |
| | | | 12 | 24.16 | 3544 | 1.04 | 957 | 676 | 34.05 | 11.80 |
| BS | | | min. | min. | min. | min. | min. | n.a | max. | |
| 5669 | | | 13.8 | 2000 | 0.34 | 470 | 360 | | 8.00 | |

Values are average of six determinations

TABLE 2
 Summary of the analysis of variance on the board properties

| SOV | Df | MOR | MOE | IB | SWS | SWE | WA | TS |
|-------------|----|----------|---------|--------|---------|---------|---------|---------|
| Age (a) | 2 | 8.95* | 3.2E6** | 0.87** | 3.6E5** | 1.2E5** | 216.9** | 22.58** |
| Density (D) | 2 | 1668.3** | 2.2E7** | 1.37** | 1.6E6** | 1.4E6** | 1972** | 514.7** |
| Resin (R) | 2 | 197.60** | 1.6E6** | 0.66** | 1.3E5** | 1.0E5** | 1517** | 888.6** |
| A x D | 4 | 58.30** | 6.5E4** | 0.00ns | 3.3E4** | 2.9E4** | 443** | 43.15** |
| A x R | 4 | 6.81* | 1.0E5** | 0.32** | 5122ns | 5014ns | 13.48ns | 2.65ns |
| D x R | 4 | 10.64** | 1.0E5** | 0.00ns | 3.6E4** | 1.1E4** | 16.23ns | 53.76** |
| A X D x R | 8 | 0.77ns | 0.00ns | 0.01ns | 5124ns | 1806ns | 46.78ns | 15.24** |

Note: ns- not significant, *- significant at P < 0.05 and **- highly significant at P < 0.01

TABLE 3
 Summaries of the Duncan multiple range t-tests on the effect of age, density and resin on the board properties

| Age (yrs) | MOR (MPa) | MOE (MPa) | IB (MPa) | SWS (N) | SWE (N) | WA (%) | TS (%) |
|------------------------------|-----------|-----------|----------|---------|---------|--------|--------|
| 1 | 17.50b | 2524b | 0.51c | 473c | 389b | 44.78a | 13.96b |
| 2 | 18.31a | 2708a | 0.78a | 592b | 472a | 46.16a | 15.36a |
| 3 | 17.17b | 2602b | 0.71b | 648a | 485a | 40.78b | 13.65b |
| Resin (%) | MOR | MOE | IB | SWS | SWE | WA | TS |
| 8 | 15.10c | 2354c | 0.47c | 484c | 374c | 50.73a | 19.35a |
| 10 | 18.20b | 2620b | 0.61b | 520b | 426b | 43.47b | 12.75b |
| 12 | 19.27a | 2736a | 0.72a | 593a | 470a | 38.84c | 10.60c |
| Density (kg/m ³) | MOR | MOE | IB | SWS | SWE | WA | TS |
| 561 | 10.88c | 1782c | 0.40c | 303c | 220c | 38.92c | 10.08c |
| 641 | 18042b | 2717b | 0.61b | 565b | 474b | 51.62a | 16.09a |
| 721 | 23.93a | 3215a | 0.76a | 699a | 564a | 41.53b | 16.10a |

Means having the same letter down the column are not significantly different (P<0.05)

The increase in strength properties could be probably associated with higher compaction ratio at higher density. Other researchers (Chen *et al.* 1991; Chew *et al.* 1992; Shaikh *et al.* 1997) also reported similar findings. Table 4 also shows that board density has a high significant correlation with the strength properties. However, the increase in board density also leads to higher TS

since a higher compressive set exists in higher density boards resulting in higher swelling as stresses are relieved (Gatchell *et al.* 1966 and Roffael and Rauch 1972).

Three Layer Particleboard

The properties of the three-layer particleboard are given in Table 5. Highest MOR (29.30 MPa)

TABLE 4
 Correlation coefficients of age, density, and resin on the properties

| SOV | MOR | MOE | IB | SWS | SWE | WA | TS |
|---------|----------|---------|--------|--------|--------|----------|----------|
| AGE | -0.01 ns | 0.07 ns | 0.43** | 0.37** | 0.25** | -0.13 ns | 0.003 ns |
| DENSITY | 0.87** | 0.89** | 0.64** | 0.79** | 0.83** | 0.11 ns | 0.46** |
| RESIN | 0.29** | 0.23** | 0.45** | 0.22** | 0.23** | -0.48** | -0.67** |

Note; SOV- source of variance, ns- not significant, * significant at P < 0.05, ** significant at P < 0.01

are exhibited by particleboard produced from 2-year-old bamboo with core particle size of 1.0 mm without wax while highest MOE (3977 Mpa) are shown by 3-year-old (1.0 mm core) with 1% wax addition. Two-year-old bamboo particles (1.0 mm core) and without wax produced particleboards with the highest IB (0.94 MPa), SWS (1013 N) and SWE (796 N) value. However they also exhibited the highest WA (70.17%). The highest TS (24.76%) value are shown by particleboards produced from 3-year-old bamboo (2.0 mm core) without wax addition. In general all boards with or without wax addition with core particles of 1.0 and 2.0 mm meet the minimum strength requirements of the BS 5669 but all boards regardless of age and wax addi-

tion failed to meet the 8% TS value stipulated in the BS 5669.

Table 6 shows the analysis of variance (ANOVA) of the board properties. All the main variables showed a significant effect on the board properties (except for core particle size on SWE and Wax on MOR). The effect of age on the dimensional and strength properties are shown in Table 7. Age had a significant effect on all the board properties. Three-year-old bamboo produces particleboard with worst WA and TS values but comparable strength properties with the other age groups. Table 8 further reveals the correlation coefficients of age on the board properties.

Core particle size (Psize) also showed a significant influence on the board properties.

TABLE 5
Strength and dimensional properties of three-layer formaldehyde-particleboard

| Age (yrs) | Psize (mm) | Wax (%) | MOR (MPa) | MOE (MPa) | IB (MPa) | SWS (N) | SWE (N) | WA (%) | TS (%) |
|-----------|------------|---------|-----------|-----------|----------|---------|---------|--------|--------|
| 1 | 1 | 1 | 29.07 | 3717 | 0.75 | 836 | 566 | 29.15 | 10.15 |
| 2 | 1 | 1 | 29.33 | 3533 | 0.58 | 755 | 557 | 36.95 | 12.78 |
| 3 | 1 | 1 | 28.34 | 3977 | 0.49 | 772 | 543 | 35.16 | 14.13 |
| 1 | 1 | 0 | 28.90 | 3539 | 0.87 | 863 | 685 | 63.86 | 19.32 |
| 2 | 1 | 0 | 29.30 | 3475 | 0.94 | 1013 | 769 | 70.17 | 20.69 |
| 3 | 1 | 0 | 28.42 | 3910 | 0.89 | 831 | 724 | 64.44 | 23.73 |
| 1 | 2 | 1 | 24.00 | 3608 | 0.48 | 827 | 531 | 30.33 | 9.45 |
| 2 | 2 | 1 | 27.32 | 3626 | 0.70 | 800 | 615 | 26.88 | 10.05 |
| 3 | 2 | 1 | 27.21 | 3756 | 0.57 | 813 | 527 | 29.97 | 11.34 |
| 1 | 2 | 0 | 25.51 | 3462 | 0.63 | 970 | 701 | 64.01 | 21.30 |
| 2 | 2 | 0 | 26.77 | 3712 | 0.84 | 1005 | 760 | 59.84 | 16.54 |
| 3 | 2 | 0 | 27.48 | 3645 | 0.87 | 939 | 732 | 67.22 | 24.76 |
| BS | 5669 | | >13.8 | >2000 | >0.34 | >470 | >360 | na | <8.00 |

Values are average of six determinations.

Psize - Core particle size

TABLE 6
Summaries of the ANOVA on the board properties

| SOV | Df | MOR | MOE | IB | SWS | SWE | WA | TS |
|-----------|----|--------|---------|--------|---------|---------|---------|---------|
| Age (A) | 2 | 9.10* | 3.8E5** | 0.04* | 1.5R4 | 1.6E* | 29.11ns | 79.70** |
| Psize (P) | 1 | 93.4** | 4.9Ens | 0.07** | 3.3E4* | 190.8ns | 192.2** | 22.54** |
| Wax (W) | 1 | 0.62ns | 9.4E4 | 0.91** | 2.8E5** | 4.4E5** | 1.7E4** | 1423** |
| A x P | 2 | 13.03* | 2.1E5** | 0.13** | 3917ns | 1668ns | 168.6** | 21.17** |
| A x W | 2 | 1.03ns | 3.9E4ns | 0.05** | 3.9E4** | 3117ns | 1.75ns | 25.46** |
| P x W | 1 | 0.63ns | 7260ns | 0.03ns | 6998ns | 22.82ns | 18.63ns | 10.74ns |
| A x P x W | 2 | 1.68ns | 1.1E4ns | 0.02ns | 9456ns | 4771ns | 31.13ns | 9.47* |

ns- not significant at P < 0.05, * - significant at P < 0.05 and ** highly significant at P < 0.01

TABLE 7
 Effect of age, particle size and wax content on the board properties

| Age (yrs) | MOR (MPa) | MOE (MPa) | IB (Mpa) | SWS (N) | SWE (N) | WA (%) | TS (%) |
|-----------|-----------|-----------|----------|---------|---------|--------|--------|
| 1 | 26.87b | 3582b | 0.68b | 874ab | 621b | | 15.06b |
| 2 | 28.16a | 3587b | 0.77a | 894a | 676a | 48.46a | 15.02b |
| 3 | 27.87ab | 3822a | 0.70b | 838b | 632ab | 49.20a | 18.49a |
| Psize(mm) | | | | | | | |
| 1.0 | 28.88a | 3692a | 0.75a | 845b | 641a | 49.96a | 16.80a |
| 2.0 | 26.38b | 3635a | 0.68b | 892a | 645a | 46.38b | 15.57b |
| Wax (%) | | | | | | | |
| 0 | 27.73a | 3624b | 0.84a | 937a | 729a | 64.92a | 21.06a |
| 1 | 27.53a | 3703a | 0.59b | 800b | 557b | 31.41b | 11.32b |

Means having the same letter down the column are not significantly different

TABLE 8
 Correlation analysis of age, particle size and wax content on the board properties

| Variable | MOR | MOE | IB | SWS | SWE | WA | TS |
|----------|---------|---------|---------|---------|---------|---------|---------|
| Age | 0.18ns | 0.50** | 0.04ns | -0.13ns | 0.04ns | 0.06ns | 0.26* |
| Psize | -0.54** | -0.14ns | -0.20ns | 0.22ns | 0.02ns | -0.10ns | -0.11ns |
| Wax | -0.04ns | 0.20ns | -0.69** | -0.63** | -0.76** | -0.96** | -0.88** |

Particleboards produced using 1.0 mm size particle gives better MOR and IB but higher WA and TS values when compared with cores produced using 2.0 mm particle size. The higher WA and TS are due to the higher surface area of the core particles produced using 1.0 mm particle size thus increasing its capacity to absorb more water. Correlation analysis from the Table 8 showed that particle size significantly decreases the MOR while the other board properties were insignificantly affected.

Wax is used to confer a degree of water repellency on the board. Table 6 shows that addition of 1% wax gives better WA and TS values. Addition of 1% wax decreases more than 50% the WA and TS. However, wax addition also decreases all the strength properties. Jamaludin *et al.* (1997) also reported a similar trend in their study. The decrease in strength properties is probably due to the resistance wax offers during gluing. Table 8 further revealed the correlation effect of wax on the board properties.

CONCLUSIONS

In the manufacture of single-layer particleboard, age, resin content and board density are found to significantly affect board properties. Particleboards produced from all age groups at

a density of over 641 kg/ m³ and at all resin contents were able to meet the strength requirements specified in BS 5669. Age, core particle size and wax affect the properties of three-layer particle board significantly. All boards made from all age groups surpassed all the strength and physical properties studied (MOR, MOE, IB, SWS and SWE) as stipulated in BS 5669. Particleboards of core particlesize of 1.0mm showed higher WA and TS values compared to particleboard of core particle size of 2.0 mm. However with 1% wax addition, the WA and TS were greatly reduced.

In terms of strength properties, all the bamboo particles from all age group of *G. schortehinii* are suitable for particleboard manufacture. However, the high values obtained for 24-hour thickness swell would require further studies before this species could be used for particleboard production.

REFERENCES

- AMINUDDIN, M and M. ABD. LATIF. 1991. Non-wood Resource and Produce of Peninsular Malaysia: Its status and Future Trends in Research. Paper presented at *Winrock International F/Fred Utilization Research Programme Development Workshop*, 21-25 January, Taipei, Taiwan.

- BS 5669: Part 2: 1989. Particleboard. Specification for Wood Chipboard and Methods of Test for Particleboard. 45 pp. London: British Standards Institution.
- CHEN, F. W., K. JAMALUDIN and L. T. CHEW. 1991. Particleboard from bamboo, FRIM Reports No. 56. Pp. 35-44. Forest Research Institute Malaysia, Kepong.
- CHEW, L. T., S. RAHIM, and K. JAMALUDIN. 1992. *Bambusa vulgaris* for urea and cementbond particleboard manufacture. *J. Trop. Forest Science* 4(3): 249-256.
- EN 310: 1993. Wood-based panels-Determination of modulus of elasticity in bending and bending strength. European Committee for Standardization. 5 pp.
- EN 317: 1993. Particleboards and fibreboards-Determination of swelling in thickness after immersion in water. European Committee of Standardization. 9 pp.
- EN 319: 1993. Particleboard and fibreboards-Determination of tensile strength perpendicular to the plane of the board. European Committee of Standardization. 11 pp.
- GATECHELL, C. J., B. G. HEEBINK and F. V. HEFTY. 1966. Influence of component variables on the properties of particleboard for exterior use. *Forest Product Journal* 16 (4): 46-59
- JAMALUDIN, K., M. ABD. LATIF, M. N. NURULHUDA and H. JAMALUDDIN. 1997. Effect of age, resin and wax contents on the properties of particleboard from 1-, 2-, 3-, and 4-y-old *Bambusa vulgaris*. *JITFP* 3(2): 178-185
- KELLY, M. W. 1976. Review of Particleboard Manufacturer and Processing. In *Wood Technology: Chemical Aspect*, ed. S. G. Irving ACS Symposium Series.
- MOSLEMI, A.A 1974. Particleboard Vol. 1: Materials, 241 pp. Southern Illinois University, USA.
- MEDWAY, L. 1973. Research at the University of Malaya Field Studies Center, Ulu Gombak-bamboo control. *Malaysian Forester* 33(1): 70-77.
- NG, F.S.P. 1980. Bamboo Research in Malaysia. In *Proceedings of the Seminar on Bamboo Research in Asia*. Lessard, G & Chouinard, A. (Eds.) Pp. 91-95 May 28-30, 1980. Singapore.
- ROFFAEL, E. and W. RAUCH. 1972. Influence of density on the swelling behaviour of phenolic resin-bonded particleboards. *Holz als Rohund Werkstoff* 30(5): 178-181.
- SALLEH, M.N. and K.M. WONG. 1987. The Bamboo Resource in Malaysia: Strategies for Development. In *Proceedings of the International Bamboo Workshop*. Rao, G. Dhanarajan and C. B. Sastry (Eds.) Pp. 45-49 October 6-14, 1985. Hangzhou, China.
- SHAIKH, A. K. Y., A. ABDUL JALIL and K. JAMALUDIN. 1997. The Properties of Particleboard from Oil Palm Empty Fruit Bunches. Paper presented at the School of Applied Science Seminar Series. MARA Institute of Technology, Shah Alam.
- TALBOTT, J.W. and T.M. MALONEY. 1997. Effect of several production variables on MOR and IB strength of boards made of Green Gouglas-fir planer shavings. *Forest Product Journal* 7(10): 395-398.

(Received: 16 January 2001)

(Accepted: 27 June 2001)